

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A mixture comprising:

(A) an isocyanurate and/or biuret of 1,6-diisocyanatohexane (HDI),

(B) an isocyanurate of 1-isocyanato-3,5,5-trimethyl-5-

isocyanatomethylcyclohexane (IPDI),

(C) at least one emulsifier, and

(D) optionally if desired, a solvent.

Claim 2 (Currently Amended): The A mixture as claimed in claim 1, wherein the at least one emulsifier ~~emulsifier(s)~~ (C) is obtained ~~is(are)-obtainable~~ by reacting at least part of the compounds (A) and/or (B) with a component (C1), containing at least one group which is reactive toward isocyanate groups and containing at least one hydrophilic group.

Claim 3 (Currently Amended): The A mixture as claimed in claim 1 ~~or~~ 2, comprising, in solvent-free form:

(A) 40 – 90% by weight,

(B) 5 – 60% by weight, and

(C1) 5 – 40% by weight,

the sum of (A), (B), and (C1) making 100% by weight, and including in each case, the isocyanate (A) and/or (B) used to prepare the emulsifier (C).

Claim 4 (Currently Amended): The A mixture as claimed in claim 3, wherein component (C1) contains at least one isocyanate-reactive group and at least one nonionic

hydrophilic group.

Claim 5 (Currently Amended): The A mixture as claimed in claim 3, wherein component (C1) is at least one polyalkylene oxide polyether alcohol, obtained ~~obtainable~~ by reacting at least one saturated aliphatic alcohol, having 1 to 4 carbon atoms in the alkyl radical, with ethylene oxide, propylene oxide or a mixture thereof.

Claim 6 (Currently Amended): The A mixture as claimed in claim 5, wherein the polyalkylene oxide polyether alcohol contains, on average, from 5 to 35 ethylene oxide units per molecule.

Claim 7 (Currently Amended): The A mixture as claimed in claim 1 ~~any of the preceding claims~~, wherein a carbonic ester or lactone is used as solvent (D).

Claim 8 (Currently Amended): The A mixture as claimed in claim 1 ~~any of the preceding claims~~, wherein the solvent is present in amounts up to 60%, by weight, based on the total mixture.

Claim 9 (Currently Amended): A polymer dispersion, comprising the ~~a~~ mixture as claimed in claim 1, and one or more additives ~~any of the preceding claims~~.

Claim 10 (Currently Amended): A coating composition, comprising the ~~a~~ mixture as claimed in claim 1, and one or more additives ~~any of claims 1 to 8 or a polymer dispersion as claimed in claim 9~~.

Claim 11 (Currently Amended): A method of coating ~~substrates~~ a substrate,
comprising, applying the mixture as claimed in claim 1, as a coating material, to the substrate
~~which comprises using a mixture as claimed in any of claims 1 to 8 as coating material.~~

Claim 12 (Currently Amended): The method of claim 11, wherein the substrate is
selected from ~~use of a mixture as claimed in any of claims 1 to 8 as a coating material for~~
wood, wood veneer, paper, paperboard, cardboard, textile, leather, nonwoven, ~~plasties~~ plastic
surfaces, glass, ceramic, mineral building materials, ~~or~~ coated metals or uncoated metals[[,]]
~~or as an adhesive.~~

Claim 13 (Currently Amended): A method of adhesively bonding substrates,
comprising, applying the mixture as claimed in claim 1, to at least one substrate ~~which~~
~~comprises using a mixture as claimed in any of claims 1 to 8 or a polymer dispersion as~~
~~claimed in claim 9.~~

Claim 14 (New): A coating composition, comprising the polymer dispersion as
claimed in claim 9, and one or more additives.

Claim 15 (New): A method of adhesively bonding substrates, comprising, applying
the polymer dispersion of claim 9, to at least one substrate.